

## Q8 Haydn 68

Advanced zinc-based hydraulic oil

### **Description**

Q8 Haydn 68 oil consists of a zinc-based additive technology. This oil can be used in all sorts of operational applications and industrial equipment. Q8 Haydn 68 oil has an optimum thermal and oxidation stability and has a long service life time.

Q8 Haydn 68 is suitable for all kinds of systems, general industrial hydraulic applications and other industrial applications (low charged gears, pumps, compressors, bearings).

- · Lower downtime and an improved maintenance efficiency
- · Zinc-based additives
- Advanced performance against wear
- · Excellent separation of water
- Advanced release of entrained air bubbles

### Specifications & Approvals

**Bosch Rexroth** RE 90220 notes **Eaton Brochure** 03-401-2010 DIN 51517-2 CL ISO 11158 HM DIN 51524-2 HLP MAG IAS P-68, P-69, P-70 Danieli Standard 0.000.001-R15 (2023) Swedish Standard SS 155434 AM

HF-0, HF-1, HF-2 Denison

### **Properties**

	Method	Unit	Typical
ISO Viscosity Grade	-	-	68
Colour	D 1500	-	2
Density, 15 °C	D 4052	g/ml	0,88
Density, 20 °C	D 4052	g/ml	0,875
Kinematic Viscosity, 40 °C	D 445	mm²/s	68
Kinematic Viscosity, 100 °C	D 445	mm²/s	8.9
Viscosity Index	D 2270	-	105
Pour Point	D 97	°C	-30
Flash Point, COC	D 92	°C	225
Emulsion, Distilled Water, 54.4 °C	D 1401	-	40-40-0(20)
Foam, 5 min blowing, seq. 1-2-3	D 892	ml	10/20/10
Foam, 10 min settling, seq. 1-2-3	D 892	ml	0/0/0
Rust Test, Proc. A and B, 24 h	D 665	-	pass
Copper Strip, 3 h, 100 °C	D 130	-	1
FZG Test, A/8.3/90	DIN 51354	load stage	12

The figures above are not a specification. They are typical figures obtained within production tolerances.

# Sustainability

The product Carbon Footprint (PCF), cradle-to-gate (Q80ils state of the art facility in Belgium), of Q8 Haydn 68 is  $1.24\,\mathrm{kg}$  CO $_2\mathrm{eq}$  / kg. Please contact Q80ils to learn more about the positive environmental impact, the

handprint, of this product. For more info check here

