

Q8 Porta 30P

Process oil with optimum performance

Description

Q8 Porta 30P is an advanced process oil with optimum performance and a high oxidation and thermal stability. This light coloured oil has a low aromatic and nitrogen content and minimum evaporation losses when heated. Q8 Porta 30P improves the elasticity of the rubber components.

Applications

Q8 Porta 30P is used in rubber and ink industry. It is applied in softeners and extenders (rubber industry). Q8 Porta 30P is also recommended as anti-dust oil in the agriculture industry and carrier oil in the lubricants industry.

Benefits

- Reduction of product portfolio through extended lubricant applications
- Highly resistant to ageing
- Optimum thermal stability
- Low evaporation

Specifications & Approvals

ISO

11158 HH

ISO

6743-4 HH

Properties

	Method	Unit	Typical
Viscosity Grade	-	-	30P
Viscosity Grade	-	-	Comparable to SN 150
Appearance	Visual	-	Bright and Clear
Colour	D 1500	-	L 2.5 max
Odor	-	-	Acceptable
Density, 15 °C	D 4052	g/ml	0,873
Kinematic Viscosity, 40 °C	D 445	mm ² /s	29.49
Kinematic Viscosity, 50 °C	D 445	mm ² /s	19.9
Kinematic Viscosity, 100 °C	D 445	mm ² /s	5.05
Viscosity Index	D 2270	-	96
Total Acid Number	D 974	mg KOH/g	<0.05
Pour Point	D 97	°C	-27
Flash Point, COC	D 92	°C	212
Flash Point, P-M	D 93	°C	203
Ash	D 482	% mass	<0.01
Sulfur	D 2622	% mass	0.5
Carbon Residue	D 524	% mass	0.01
Water content	D 1744	ppm	100
DMSO extract	IP 346	%	<1
Hydrocarbons: Aromatic Rings	D 2140	%	4.3
Hydrocarbons: Naphthenic Rings	D 2140	%	33.1
Hydrocarbons: Paraffinic Chains	D 2140	%	62.6
Refractive Index n ₂₀ /D	D 1218	-	1.479
Refractivity Intercept	D 2140	-	1.045
Aniline Point	D 611	°C	98.5
Clay-gel adsorption: Aromatics	D 2007	% mass	25.9
Clay-gel adsorption: Asphaltenes	D 2007	% mass	<0.1
Clay-gel adsorption: Polar Compounds	D 2007	% mass	0.7
Clay-gel adsorption: Saturates	D 2007	% mass	83.5
Noack volatility	D 5800	%	15
Shear Stability	CEC L-14-93	%	2 max

The figures above are not a specification. They are typical figures obtained within production tolerances.

Sustainability

The product Carbon Footprint (PCF), cradle-to-gate (Q8Oils state of the art facility in Belgium), of Q8 Porta 30P is **1.21 kg CO₂eq / kg**.

Please contact Q8Oils to learn more about the positive environmental impact, the handprint, of this product.

For more info check here



**we
take
care**